



# Standard Specification for Nickel-Iron-Chromium Alloy Seamless Pipe and Tube<sup>1</sup>

This standard is issued under the fixed designation B 407; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification<sup>2</sup> covers UNS N08120, UNS N08800, UNS N08801, UNS N08810, UNS N08811, UNS N08890, and UNS N06811 in the form of cold-worked and hot-finished annealed seamless pipe and tube. Alloys UNS N08800 and UNS N06811 are normally employed in service temperatures up to and including 1100°F (593°C). Alloys UNS N08120, UNS N08810, UNS N08811, and UNS N08890 are normally employed in service temperatures above 1100°F (593°C) where resistance to creep and rupture is required, and they are annealed to develop controlled grain size for optimum properties in this temperature range.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following safety hazards caveat pertains only to the test method portion, Section 13, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

**B 880** Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys

**E 8** Test Methods for Tension Testing of Metallic Materials

**E 18** Test Methods for Rockwell Hardness of Metallic Materials

**E 29** Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

**E 112** Test Methods for Determining Average Grain Size

**E 140** Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, and Scleroscope Hardness

**E 426** Practice for Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys

**E 571** Practice for Electromagnetic (Eddy-Current) Examination of Nickel and Nickel Alloy Tubular Products

**E 1473** Test Methods for Chemical Analysis of Nickel, Cobalt, and High-Temperature Alloys

## 3. Terminology

### 3.1 Definitions:

3.1.1 *average diameter, n*—average of the maximum and minimum outside diameters, or the maximum and minimum inside diameters, as determined at any one cross section of the tube.

3.1.2 *pipe, n*—seamless tube conforming to the particular dimensions commercially known as standard pipe sizes (see **Table X3.1**).

3.1.3 *tube, n*—hollow product of round or any other cross section having a continuous periphery.

## 4. Ordering Information

4.1 Orders for material to this specification should include information with respect to the following:

4.1.1 Alloy (**Table 1**).

4.1.2 Condition Temper (**Table 2** and **Table X3.1**, and **Appendix X2** and **Appendix X3**).

4.1.3 Finish (**Table X1.1** and **Table X3.2**).

4.1.4 *Dimensions:*

4.1.4.1 *Tube*—May be specified in two dimensions only (length excepted) as follows: Outside diameter and average or minimum wall, inside diameter and average wall, or outside diameter and inside diameter.

NOTE 1—Tube produced to outside diameter and minimum wall may be furnished upon agreement between the manufacturer and the purchaser.

4.1.4.2 *Pipe*—Standard pipe size and schedule (**Table X3.1**).

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved March 1, 2008. Published April 2008. Originally approved in 1957. Last previous edition approved in 2004 as B 407 – 04.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SB-407 in Section II of that Code.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

**TABLE 1 Chemical Requirements**

Element	Composition Limits, %				
	UNS N08120	UNS N08800, UNS N08810, and UNS N08811	UNS N08801	UNS N08890	UNS N06811
Nickel	35.0 min 39.0 max	30.0 min 35.0 max	30.0 min 34.0 max	40.0 min 45.0 max	38.0 min 46.0 max
Chromium	23.0 min 27.0 max	19.0 min 23.0 max	19.0 min 22.0 max	23.5 min 28.5 max	27.0 min 31.0 max
Iron	remainder	39.5 min <sup>A</sup>	39.5 min <sup>A</sup>	remainder	remainder
Manganese, max	1.5	1.5	1.5	1.5	2.0
Carbon	0.02 min 0.10 max	<sup>B</sup>	0.10 max ...	0.06 min 0.14 max	0.03 max ...
Copper, max	0.5	0.75	0.5	0.75	...
Silicon	1.0 ...	1.0 ...	1.0 ...	1.0 min 2.0 max	0.60 max ...
Sulfur, max	0.03	0.015	0.015	0.015	0.010
Aluminum <sup>C</sup>	0.40 max ...	0.15 min 0.60 max	...	0.05 min 0.60 max	...
Titanium <sup>C</sup>	0.20 max ...	0.15 min 0.60 max	0.75 min 1.50 max	0.15 min 0.60 max	...
Columbium	0.4 min 0.9 max	...	...	...	...
Molybdenum	2.50 max ...	...	...	1.0 min 2.0 max	0.50 min 1.50 max
Niobium	...	...	...	0.2 min 1.0 max	...
Tantalum	...	...	...	0.10 min 0.60 max	...
Phosphorus	0.040 max	...	...	...	0.030 max
Tungsten	2.50 max	...	...	...	...
Cobalt, max	3.0	...	...	...	...
Nitrogen	0.15 min 0.30 max	...	...	...	0.10 min 0.20 max
Boron	0.010 max	...	...	...	...

<sup>A</sup> Iron shall be determined arithmetically by difference.

<sup>B</sup> Alloy UNS N08800: 0.10 max. Alloy UNS N08810: 0.05–0.10. Alloy UNS N08811: 0.06–0.10.

<sup>C</sup> Alloy UNS N08811: Al + Ti, 0.85–1.20.

**TABLE 2 Mechanical Properties<sup>A,B</sup> of Pipe and Tube**

Alloy	Condition (Temper)	Tensile Strength, min, psi (MPa)	Yield Strength, (0.2 % offset), min, psi (MPa)	Elongation in 2 in. or 50 mm (or 4D), min, %
UNS N08120	hot-finished annealed or cold-worked annealed	90 000 (621)	40 000 (276)	30
UNS N08800	cold-worked annealed	75 000 (520)	30 000 (205)	30
UNS N08800	hot-finished annealed or hot-finished	65 000 (450)	25 000 (170)	30
UNS N08810 and UNS N08811	hot-finished annealed or cold-worked annealed	65 000 (450)	25 000 (170)	30
UNS N08801	hot-finished annealed or cold-worked annealed	65 000 (450)	25 000 (170)	30
UNS N08890	hot-finished annealed or cold-worked annealed	75 000 (520)	30 000 (205)	35
UNS N06811	hot-finished annealed or cold-worked annealed	85 000 (585)	35 000 (240)	30

<sup>A</sup> For properties of small-diameter and light-wall tubing, see [Table X3.1](#).

<sup>B</sup> See [13.3](#).

4.1.5 *Fabrication Details*—Not mandatory but helpful to the manufacturer:

4.1.5.1 Cold Bending or Coiling.

4.1.5.2 Hot Forming.

4.1.5.3 *Welding or Brazing*—Process to be employed.

4.1.5.4 *Pressure Requirements*—Test pressure if other than required by [7.3](#).

4.1.5.5 *Machining*—Indicate finished size and length in which to be machined and whether to be chucked to outside diameter or inside diameter.

4.1.5.6 *Ends*—Plain ends cut and deburred will be furnished. If threaded ends or ends beveled for welding are desired, give details.

4.1.6 *Certification*—State if certification or a report of test results is required ([Section 16](#)).

4.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished ([6.2](#)).

4.1.8 *Purchaser Inspection*—If the purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed ([Section 14](#)).

4.1.9 *Small-Diameter and Light-Wall Tube*—(Converter Sizes) ([Table X3.2](#)).

4.1.10 *Optional Requirement*—Hydrostatic or Nondestructive Eddy Current Testing (see [7.3.3](#)).

## 5. Materials and Manufacture

5.1 *Heat Treatment*—The final heat treatment of UNS N08120 shall be 2150°F (1177°C) minimum, UNS N08810,

2050°F (1121°C) minimum, UNS N08811, UNS N08890, 2100°F (1149°C) minimum, and UNS N06811, 1920°F (1050°C) minimum.

## 6. Chemical Composition

6.1 The material shall conform to the composition limits specified in **Table 1**.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in Specification **B 880**.

## 7. Mechanical Properties and Other Requirements

7.1 *Mechanical Properties*—The material shall conform to the mechanical properties specified in **Table 2**.

7.2 *Grain Size*—Annealed UNS Alloys N08120, N08810, N08811, and UNS N08890 shall conform to an average grain size of ASTM No. 5 or coarser.

### 7.3 Hydrostatic Test:

7.3.1 Each pipe or tube with an outside diameter 1/8 in. (3.2 mm) and larger, and tubes with wall thickness of 0.015 in. (0.38 mm) and over shall be tested by the manufacturer to an internal hydrostatic pressure of 1000 psi (6.9 MPa) provided that the fiber stress calculated in accordance with the following equation does not exceed the allowable fiber stress, *S*, indicated below. The pipe or tube shall show no evidence of leakage.

$$P = 2St/D$$

where:

*P* = hydrostatic test pressure, psi (MPa),

*S* = allowable fiber stresses, for material in the condition, as follows:

Cold-drawn annealed or hot-finished annealed alloy UNS N08120	22 500 psi 155 (MPa)
Cold-drawn annealed alloy UNS N08800 and all alloy UNS N08890	18 700 psi (130 MPa)
Hot-finished as hot-finished, or hot-finished annealed, alloy UNS N08800	16 600 psi (115 MPa)
Cold-drawn annealed or hot-finished annealed alloys UNS N08810, UNS N08811, and UNS N08801	16 600 psi (115 MPa)
Cold-drawn annealed or hot-finished annealed alloy UNS N06811	21 200 psi (145 MPa)

*t* = minimum wall thickness, in. (mm), equal to the specified average wall thickness minus the permissible minus wall tolerance, **Table 3**, or the specified minimum wall thickness, and

*D* = outside diameter of the tube, in. (mm).

7.3.2 When so agreed upon between the manufacturer and purchaser, pipe or tube may be tested to 1½ times the allowable fiber stress given in **7.3.1**.

7.3.3 Each pipe or tube shall be subjected to the hydrostatic test, or, in lieu of this test, a nondestructive eddy current test may be used at the manufacturer's option. If eddy current testing is used, the following test method would apply:

7.3.3.1 *Eddy-Current Testing*—Testing shall be conducted in accordance with Practices **E 426** or **E 571**. The eddy-current examination referenced in this specification has the capability of detecting significant discontinuities, especially of the short abrupt type.

(1) Unless otherwise specified the calibration standard shall contain, at the option of the manufacturer, any one of the

following discontinuities to establish a minimum sensitivity level for rejection. The discontinuity shall be placed in the weld if visible.

(2) *Drilled Hole*—A hole not larger than 0.031 in. (0.79 mm) in diameter shall be drilled radially and completely through the wall, care being taken to avoid distortion of the material while drilling.

(3) *Transverse Tangential Notch*—Using a round file or tool with a 1/4 in. (6 mm) diameter, a notch shall be filed or milled on the tube outside diameter tangential to the surface and transverse to the longitudinal axis of the material. Said notch shall have a depth not exceeding 12½ % of the specified wall thickness of the material, or 0.004 in. (0.10 mm), whichever is greater.

7.3.3.2 *Calibration Frequency*—The frequency of calibration checks shall be as follows:

(1) At the beginning of each production run or log.

(2) After every 4 h or less during testing.

(3) At the end of each production run or lot.

(4) At any time malfunctioning is suspected, or the equipment has been left unattended.

(5) If, during any check, the equipment fails to pick up the standard defects in the calibration standard, the instrument test must be recalibrated and all material tested since the last check shall be reexamined.

7.3.3.3 *Acceptance and Rejection*—Material producing a signal equal to or greater than the calibration imperfection shall be subject to rejection.

(1) Test signals produced by imperfections that cannot be identified or produced by cracks or crack-like imperfections shall result in rejection of the tube, subject to rework, and retest.

(2) If the imperfection is judged as not fit for use, the tube shall be rejected, but may be reconditioned and retested providing the dimensions requirements are met. To be accepted, retested material shall meet the original electric test requirements.

(3) If the imperfection is explored to the extent that it can be identified and the pipe or tube is determined to be fit for use, the material may be accepted without further test providing the imperfection does not encroach on the minimum wall thickness.

7.4 *Annealing Temperature*—Alloy UNS N08120 shall be annealed at 2150°F (1177°C) minimum, and UNS N08810 at 2050°F (1120°C) minimum.

## 8. Dimensions and Permissible Variations

### 8.1 Diameter and Wall Thickness:

8.1.1 The permissible variations in the outside and inside diameter and wall thickness of pipe and tube shall not exceed those prescribed in **Table 3** and **Table X3.2**, as applicable.

8.1.2 Permissible variations given in **Table 3** and **Table X3.2** are applicable only to two dimensions. Thus, if outside diameter and wall are specified, the inside diameter may not conform to the permissible variations shown. Similarly, if outside diameter and inside diameter are specified, the wall may not conform to the permissible variations shown.

8.2 *Length*—When pipe or tube is ordered cut-to-length, the length shall not be less than that specified, but a variation of

**TABLE 3 Permissible Variations in Outside and Inside Diameter and Wall Thickness (Average Wall)**

Specified Outside Diameter or Calculated Nominal Outside Diameter (When Ordered to Inside Diameter and Average Wall)	Permissible Variations			
	Outside Diameter or Inside Diameter		Wall Thickness, %	
	+	-	+	-
Cold-Finished <sup>A,B,C,D</sup> Pipe and Tube				
Inches				
0.500 to 5/8, excl	0.005	0.005	15.0	15.0
5/8 to 1 1/2, incl	0.0075	0.0075	10.0	10.0
Over 1 1/2 to 3 1/2, incl	0.010	0.010	10.0	10.0
Over 3 1/2 to 4 1/2, incl	0.015	0.015	10.0	10.0
Over 4 1/2 to 6, incl	0.020	0.020	12.5	12.5
Over 6 to 6 5/8, incl	0.025	0.025	12.5	12.5
Millimetres				
12.7 to 15.8, excl	0.127	0.127	15.0	15.0
15.8 to 38.1, incl	0.190	0.190	10.0	10.0
Over 38.1 to 88.9, incl	0.254	0.254	10.0	10.0
Over 88.9 to 114.3, incl	0.381	0.381	10.0	10.0
Over 114.3 to 152.4, incl	0.508	0.508	12.5	12.5
Over 152.4 to 168.3, incl	0.635	0.635	12.5	12.5
Hot-Finished Tube <sup>E,F,G,H</sup>				
Inches				
2 1/2 to 5 1/2, excl	0.031	0.031	12.5	12.5
5 1/2 to 9 1/4, incl	0.047	0.047	12.5	12.5
Millimetres				
63.5 to 139.7, excl	0.787	0.787	12.5	12.5
139.7 to 234.9, incl	1.19	1.19	12.5	12.5

<sup>A</sup> The permissible variations in this table apply to individual measurements, including out-of-roundness (ovality), except for the following conditions.

1) *Thin-Wall Pipe and Tube*—For thin-wall pipe and tube having a nominal wall thickness of 3 % or less of the nominal outside diameter, in all conditions (temper), the mean outside diameter or mean inside diameter shall conform to the permissible variations of this table, and individual measurements (including ovality) shall conform to the plus and minus values of this table, with the values increased by 0.5 % of the nominal outside diameter.

2) *Annealed Pipe and Tube Over 4 1/2 in. (114.3 mm) in Nominal Outside Diameter*—For annealed pipe and tubing over 4 1/2 in. (114.3 mm) in nominal outside diameter with a nominal wall thickness greater than 3 % of the nominal outside diameter, the mean outside diameter or mean inside diameter shall conform to the permissible variations of this table, and individual measurements shall not exceed twice the permissible variations of this table.

<sup>B</sup> For pipe and tube, in all tempers, with an inside diameter of less than 1/2 in. (12.70 mm) which cannot be successfully drawn over a mandrel, the inside diameter shall be governed by the outside diameter and the wall thickness variations.

<sup>C</sup> For pipe and tube in all tempers with an inside diameter less than 50 % of the outside diameter, which cannot be successfully drawn over a mandrel, the inside diameter may vary over or under by an amount equal to 10 % of the nominal wall thickness and the wall thickness may vary  $\pm 15$  %.

<sup>D</sup> *Eccentricity*—The variation in wall thickness in any one cross section of any one cold-finished pipe or tube shall not exceed  $\pm 10$  % of the actual (measured) average wall of that section (defined as the average of the thickest and the thinnest wall in that section).

<sup>E</sup> For tube 5 in. (127.0 mm) and under in outside diameter the tolerance on the outside diameter applies for individual measurements and includes ovality. For tubes over 5 in. (127.0 mm) in outside diameter the mean outside diameter shall conform to the permissible variations of this table and individual measurements shall not exceed twice the permissible variations of this table.

<sup>F</sup> The diameter tolerances for tube with machined outside and inside diameters shall be +0.031 in. (0.787 mm), -0 for the outside diameter and +0, - 0.062 in. (1.57 mm) for the inside diameter.

<sup>G</sup> If tube is specified as minimum wall, the tolerance shall be +28.5 %, -0.

<sup>H</sup> The wall thickness tolerance includes eccentricity tolerance up to  $\pm 12.5$  %.

+1/8 in. (3.2 mm) will be permitted for cold-worked material and +3/16 in. (4.8 mm) for hot-finished tube, except that for lengths over 30 ft (9.1 m), a variation of +1/4 in. (6.4 mm) will be permitted. For small-diameter and light-wall tube, material shall conform to the applicable requirements of **Table X3.2**.

8.3 *Straightness*—Cold-drawn material shall be reasonably straight and free of bends and kinks. For small-diameter and light-wall tube, material shall conform to the applicable requirements of **Table X3.2**. The camber (depth of chord) of hot-finished tube 5 in. (127 mm) in outside diameter and under shall not exceed 0.01 in./ft (0.8 mm/m). For sizes over 5 in. in outside diameter, the camber shall not exceed 0.015 in./ft (1.4 mm/m).

## 9. Workmanship, Finish, and Appearance

9.1 The material shall be uniform in quality and temper, smooth, commercially straight, and free of injurious imperfections.

## 10. Sampling

10.1 *Lot*:

10.1.1 A lot for chemical analysis shall consist of one heat.

10.1.2 A lot for mechanical properties and grain size testing shall consist of all material from the same heat, nominal size (excepting length), and condition (temper).

10.1.2.1 Where material cannot be identified by heat, a lot shall consist of not more than 500 lb (227 kg) of material in the same condition (temper) and nominal size (excepting length).

### 10.2 Test Material Selection:

10.2.1 *Chemical Analysis*—Representative samples shall be taken during pouring or subsequent processing.

10.2.1.1 Product (check) analysis shall be wholly the responsibility of the purchaser.

10.2.2 *Mechanical Properties and Grain Size*—Samples of the material to provide test specimens for mechanical properties and grain size shall be taken from such locations in each lot as to be representative of that lot.

## 11. Number of Tests

11.1 *Chemical Analysis*—One test per lot.

11.2 *Mechanical Properties*—One test per lot.

11.3 *Grain Size*—One test per lot.

11.4 *Hydrostatic or Eddy Current*—Each piece per lot.



## 12. Specimen Preparation

12.1 Tension test specimens shall be taken from material in the final condition (temper) and tested in the direction of fabrication.

12.2 Whenever possible, all pipe and tube shall be tested in full tubular size. When testing in full tubular size is not possible, longitudinal strip specimens, or the largest possible round specimen, shall be used. In the event of disagreement when full tubular testing is not possible, a longitudinal strip specimen with reduced gage length as contained in Test Methods **E 8** shall be used.

## 13. Test Methods

13.1 The chemical composition, mechanical, and other properties of the material as enumerated in this specification shall be determined, in case of disagreement, in accordance with the following methods:

Test Method	ASTM Designation
Chemical Analysis	<b>E 1473</b>
Tension	<b>E 8</b>
Rounding Procedure	<b>E 29</b>
Rockwell Hardness	<b>E 18</b>
Grain Size	<b>E 112</b>
Hardness Conversion	<b>E 140</b>

13.2 The measurement of average grain size may be carried out by the planimetric method, the comparison method, or the intercept method described in Test Methods **E 112**. In case of dispute, the “referee” method for determining average grain size shall be the planimetric method.

13.3 For purposes of determining compliance with the specified limits for requirements of the properties listed in the following table, an observed value, or a calculated value, shall be rounded as indicated below, in accordance with the rounding method of Practice **E 29**:

Test	Rounded Unit for Observed or Calculated Value
Chemical composition, hardness, and tolerances (when expressed in decimals)	nearest unit in the last right-hand place of figures of the specified limit
Tensile strength, yield strength	nearest 1000 psi (6.9 MPa)
Elongation	nearest 1 %
Grain size:	
0.0024 in. (0.060 mm) or larger	nearest multiple of 0.0002 in. (0.005 mm)
less than 0.0024 in. (0.060 mm)	nearest multiple of 0.0001 in. (0.002 mm)

## 14. Inspection

14.1 Inspection of the material shall be made as agreed upon between the manufacturer and the purchaser as part of the purchase contract.

## 15. Rejection and Rehearing

15.1 Material not conforming to this specification or to authorized modifications will be subject to rejection.

15.2 Samples tested in accordance with this specification that represent rejected material shall be preserved for not less than 3 weeks from the date of the test report. In case of dissatisfaction with the results of the tests, the manufacturer may make claim for a rehearing within that time.

## 16. Certification

16.1 When specified in the purchase order or contract, a manufacturer’s certification shall be furnished to the purchaser stating that material has been manufactured, tested, and inspected in accordance with this specification, and that the test results on representative samples meet specification requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

## 17. Product and Package Marking

17.1 *Product Marking*—The name or brand of the manufacturer, the trade name of the material or UNS number, the letters ASTM, the specification number, heat number and nominal size shall be legibly marked on each piece  $\frac{3}{4}$  in. (19.1 mm) and over in outside diameter, provided the length is not under 3 ft (914 mm). The material marking shall be by any method which will not result in harmful contamination.

17.1.1 For material less than  $\frac{3}{4}$  in. (19.1 mm) in outside diameter and material under 3 ft (914 mm) in length, the information in **17.1** shall be either stenciled or marked on a tag securely attached to the bundle or box in which the material is shipped.

17.2 *Package Marking*—Each bundle or shipping container shall be marked with the name or brand of the manufacturer, the trade name of the material or UNS number, the letters ASTM, the specification number, heat number, condition and nominal size, net weight, consignor and consignee address, contract or order number, or other such information as may be defined in the contract or order.

## 18. Keywords

18.1 seamless pipe; seamless tube; UNS N08120; UNS N08800; UNS N08801; UNS N08810; UNS N08811; UNS N08890; UNS N06811

**APPENDIXES**
**(Nonmandatory Information)**
**X1. SCHEDULES OF COLD-DRAWN, SEAMLESS NICKEL-IRON-CHROMIUM ALLOY PIPE**

X1.1 The schedules of cold-worked, seamless nickel-iron-chromium alloy pipe as given in **Table X1.1** are regularly available. Other schedules may be furnished, and the manufacturer should be consulted. **Table X1.1** is published for information only.

**TABLE X1.1 Pipe Schedules<sup>A</sup>**

Nominal Pipe Size	Outside Diameter	Nominal Wall Thickness			
		Schedule No. 5	Schedule No. 10	Schedule No. 40	Schedule No. 80
Inches					
1/4	0.540	...	0.065	0.088	...
3/8	0.675	...	0.065	0.091	0.126
1/2	0.840	0.065	0.083	0.109	0.147
3/4	1.050	0.065	0.083	0.113	0.154
1	1.315	0.065	0.109	0.133	0.179
1 1/4	1.660	0.065	0.109	0.140	0.191
1 1/2	1.900	0.065	0.109	0.145	0.200
2	2.375	0.065	0.109	0.154	0.218
2 1/2	2.875	0.083	0.120	0.203	0.276
3	3.500	0.083	0.120	0.216	0.300
3 1/2	4.000	0.083	0.120	0.226	0.318
4	4.500	0.083	0.120	0.237	0.337
5	5.563	...	...	0.258	...
6	6.625	...	...	0.280	...
Millimetres					
6.35	13.72	...	1.65	2.24	...
9.52	17.14	...	1.65	2.31	3.20
12.70	21.34	1.65	2.11	2.77	3.73
19.05	26.67	1.65	2.11	2.87	3.91
25.4	33.40	1.65	2.77	3.38	4.55
31.8	42.16	1.65	2.77	3.56	4.85
38.1	48.26	1.65	2.77	3.68	5.08
50.8	60.32	1.65	2.77	3.91	5.54
63.5	73.02	2.11	3.05	5.16	7.04
76.2	88.90	2.11	3.05	5.49	7.62
88.9	101.60	2.11	3.05	5.74	8.08
101.6	114.30	2.11	3.05	6.02	8.56
127.0	141.30	...	...	6.55	...
152.4	168.28	...	...	7.11	...

<sup>A</sup> The pipe schedules shown above conform with standards adopted by the American National Standards Institute.

## X2. CONDITIONS AND FINISHES NORMALLY SUPPLIED

X2.1 This appendix lists the conditions and finishes in which pipe and tube (other than converter sizes) are normally supplied. These are subject to change and the manufacturer should be consulted for the latest information available.

### X2.2 Cold-Finished Tube and Pipe:

X2.2.1 *Cold-Finished, Annealed, with Ground Outside Diameter*—The inside diameter may have a bright finish when material is annealed in a protective atmosphere; otherwise, the inside diameter is supplied descaled as necessary. Available in sizes ½ to 4 in. (12.7 to 102 mm), inclusive, in outside diameter in both normal and heavy-wall tube, and pipe sizes, all schedules, of corresponding outside diameter dimensions.

X2.2.2 *Cold-Finished, Annealed, and Pickled (Not Ground)*—Outside and inside diameter will have dull, matte (pickled) surfaces. Available in sizes ½ to 6<sup>5</sup>/<sub>8</sub> in. (12.7 to 168 mm), inclusive, in outside diameter in both normal and

heavy-wall tube, and pipe sizes, all schedules, of corresponding outside diameter dimensions.

### X2.3 Hot-Finished Tube:

X2.3.1 *Hot-Finished, or Hot-Finished Annealed (Not Pickled) Tube*—Has an oxide surface resulting from the hot-finishing operation. Intended generally for machined parts where the oxide surface will be removed.

X2.3.2 *Hot-Finished, or Hot-Finished Annealed (Pickled) Tube*—Has the oxide surface removed on both outside and inside diameters by pickling. Surface may be spot ground for removal of minor surface imperfections at the manufacturer's option.

X2.3.3 *Hot-Finished, or Hot-Finished Annealed (Machined Outside and Inside Diameters) Tube*—The outside and inside diameter surfaces are machined to specified dimensions. Minor surface imperfections may be spot ground for removal, at the manufacturer's option.

## X3. CONVERTER SIZES (ALLOY (UNS N08800) ONLY)

X3.1 Small diameter and light-wall tube in outside diameters 1¼ in. (31.8 mm) and under may be furnished in the following conditions or tempers shown in [Table X3.1](#) and [Table X3.2](#) when so specified. The material is furnished in a limited range of sizes and the manufacturer should be consulted as to the various outside diameters and wall thicknesses that may be furnished. Material will have a bright finish. Such material shall conform to the applicable requirements for the conditions indicated in [Table X3.1](#) and [Table X3.2](#).

**TABLE X3.1 Mechanical Properties<sup>A</sup> of Small-Diameter and Light-Wall Tubing (Converter Sizes) (Alloy UNS N08800)**

Material	Tensile Strength, min, psi (MPa)	Yield Strength (0.2 % offset) <sup>B</sup> , min, psi (MPa)	Elongation in 2 in. or 50 mm, min, %	Rockwell Hardness <sup>C</sup> (or Equivalent)
Annealed <sup>D,E</sup>	75 000 to 100 000 (520 to 690)	30 000 (205)	30	B95 max
Half-hard <sup>F</sup>	105 000 (725)	60 000 (415)	13	B93 to C26
Full-hard <sup>G</sup>	130 000 (895)	105 000 (725)	4	C24 to C38

<sup>A</sup> Not applicable to outside diameters under ⅜ in. (3.18 mm) and to wall thickness under 0.015 in. (0.381 mm).

<sup>B</sup> See 13.3.

<sup>C</sup> Hardness values, indicative of tensile strength, are shown for information only. All tests are subject to confirmation by tension tests. For hardness conversions see Hardness Conversion Tables E 140.

<sup>D</sup> This condition is sometimes designated as "No. 1 Temper."

<sup>E</sup> The minimum tensile strength value applies only to tubing in straight lengths.

<sup>F</sup> This condition is sometimes designated as "No. 2 Temper."

<sup>G</sup> This condition is sometimes designated as "No. 3 Temper."

**TABLE X3.2 Permissible Variations for Small-Diameter and Light-Wall Tube (Converter Sizes)<sup>A,B,C,D,E,F,G,H</sup>**

Specified Outside Diameter	Outside Diameter		Inside Diameter		Wall Thickness, %	
	+	-	+	-	+	-
Inches						
Under 3/32	0.002	0	0	0.002	10	10
3/32 to 3/16 (0.1875), excl	0.003	0	0	0.003	10	10
3/16 to 1/2 (0.500), excl	0.004	0	0	0.004	10	10
1/2 to 1 1/4 (1.250), incl	0.005	0	0	0.005	10	10
Millimetres						
Under 2.38	0.051	0	0	0.051	10	10
2.38 to 4.76, excl	0.076	0	0	0.076	10	10
4.76 to 12.70, excl	0.102	0	0	0.102	10	10
12.70 to 31.8, incl	0.127	0	0	0.127	10	10
Length, ft	Tube Size, in.	Permissible Variations, in.				
		Over		Under		
Under 1	up to 1.250, incl	1/32		0		
1 to 4, incl	up to 1.250, incl	1/16		0		
Over 4 to 10, incl	up to 1.250, incl	3/32		0		
Over 10	up to 1.250, incl	3/16		0		
Length, cm	Tube Size, mm	Permissible Variations, mm				
		Over		Under		
Under 30	up to 31.75, incl	0.794		0		
30 to 122, incl	up to 31.75, incl	1.59		0		
Over 122 to 300, incl	up to 31.75, incl	2.38		0		
Over 300	up to 31.75, incl	4.76		0		

<sup>A</sup> Ovality, Normal Wall Tube:

*Annealed (No. 1) Temper*—Ovality will be held within 2 % of the theoretical average outside diameter.

<sup>B</sup> Ovality, Light-Wall Tube:

*Annealed (No. 1) Temper*—Ovality will be held within 3 % of the theoretical average outside diameter.

<sup>C</sup> Wall Tolerances, Light-Wall Tube—The plus and minus wall tolerance shown in the table shall apply down to and including 0.005 in. (0.127 mm) in wall thickness. For wall thicknesses less than 0.005 in. (0.1 mm) the tolerance shall be  $\pm 0.0005$  in. (0.0127 mm).

<sup>D</sup> Random Lengths—Where nominal random lengths on tubing 1/8 in. (3.18 mm) and larger in outside diameter are specified, a length tolerance of  $\pm 3\frac{1}{2}$  ft (106 cm) applies to the nominal length. This is a total spread of 7 ft (210 cm).

Random lengths in sizes 1/8 in. (3.18 mm) and larger in outside diameter shall be subject to a length range of 5 to 24 ft (150 to 730 cm). Long random lengths are subject to a range of 15 to 22 ft (457 to 670 cm).

Random lengths in sizes up to, but not including 1/8 in. (3.18 mm) in outside diameter, and fragile light-wall tubes over this outside diameter are subject to the length range of 1 to 15 ft (30 to 457 cm).

<sup>E</sup> Cut Lengths—Tolerances on cut lengths shall be as follows:

<sup>F</sup> Straightness—Round tubing is subject to a straightness tolerance of one part in 600 (equivalent to a depth of arc of 0.030 in. (0.762 mm) in any 3 ft (91 cm) of length).

<sup>G</sup> Eccentricity—Eccentricity as defined in Table 3, Footnote D shall be limited to  $\pm 10$  % of the specified wall or calculated average wall.

<sup>H</sup> When specified, the tolerance spreads of this table may be applied as desired. However, when not specified, the tolerances in this table will apply. It should be noted that inside diameter tolerances are based upon the outside diameter range.

## SUMMARY OF CHANGES

Committee B02 has identified the location of selected changes to this standard since the last issue (B 407 - 04) that may impact the use of this standard. (Approved March 1, 2008.)

(I) Revised chemistry of N06811 in Table 1.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*